

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES


Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**



Patent
Attorney's Docket No. 001425-104

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Patent Application of)

Masahiko TANAKA et al.)

Application No.: 09/862,458)

Filed: May 23, 2001)

For: THIN-FILM DISPOSITION
APPARATUS)

Group Art Unit: 1763

Examiner: Karla A. Moore

Confirmation No.: 7476

#4
2/11/03
MW

RECEIVED
FEB 10 2003
TC 1700 MAIL ROOM

SUBMISSION OF VERIFIED TRANSLATION

Assistant Commissioner for Patents
Washington, D.C. 20231

Sir:

Submitted herewith is a translation of Japanese Patent No. 2000-188667, together
with a verification of the translation.


Respectfully submitted,

BURNS, DOANE, SWECKER & MATHIS, L.L.P.

By: William C. Rowland
William C. Rowland
Registration No. 30,888

P.O. Box 1404
Alexandria, Virginia 22313-1404
(703) 836-6620

Date: February 6, 2003



1946

RECEIVED
FEB 10 2003
TC 1700 MAIL ROOM

RWS Group plc, of Europa House, Marsham Way, Gerrards Cross, Buckinghamshire, England, hereby declares that, to the best of its knowledge and belief, the following document, prepared by one of its translators competent in the art and conversant with the English and Japanese languages, is a true and correct translation of the accompanying documents in the Japanese language.

Signed this 14th day of March 2001

S. POTTS

Director

For and on behalf of RWS Group plc

[Document Title] Specification

[Title of the Invention] Thin-film deposition apparatus

[Scope of Patent Claims]

[Claim 1] A thin-film deposition apparatus, wherein the
5 interior of a vacuum reaction chamber is divided by a
dividing plate into a plasma discharge space and a film
deposition process space, the said dividing plate having
internal spaces therein - which are separated from said
plasma discharge space and are connected with said film
10 deposition process space - and a plurality of holes which
connect the said plasma discharge space with the said film
deposition process space, and wherein a gas is introduced
into the said plasma discharge space where a plasma is used
to generate radicals, these radicals are introduced into the
15 said film deposition process space through the plurality of
holes in the said dividing plate, and a precursor gas is
directly introduced into the said film deposition process
space, whereby the said radicals and precursor gas
introduced into the film deposition process space react
20 together to deposit a film on a substrate disposed in the
film deposition process space,

characterized in that the said dividing plate is made
by fixing or connecting together a plurality of laminated
plates by securely bonding them over the entire area of
25 their interfacial surfaces.

[Claim 2] A thin-film deposition apparatus according to
Claim 1, characterized in that the dividing plate is fixed
by caulking with a plurality of metal fixings to securely
bond the plurality of laminated plates over the entire area
30 of their interfacial surfaces, and in that the said
plurality of holes provided in this dividing plate are
provided through the said plurality of metal fixings.

[Claim 3] A thin-film deposition apparatus according to
Claim 1, characterized in that the dividing plate is fixed
35 and configured by screwing a plurality of metal fixings
provided with threaded parts on the outside thereof into the
plurality of laminated plates, thereby securely bonding them
over the entire area of their interfacial surfaces, and in
that the said plurality of holes provided in this dividing

plate are provided through the said plurality of metal fixings.

[Claim 4] A thin-film deposition apparatus according to Claim 1, characterized in that the dividing plate is made by connecting together a plurality of laminated plates by securely bonding them over the entire area of their interfacial surfaces, and in that the said plurality of holes provided in this dividing plate are formed by piercing through it at positions where the abovementioned internal spaces are not disposed.

[Claim 5] A thin-film deposition apparatus according to any one of Claims 1 to 4, characterized in that the plurality of holes are formed so as to satisfy the condition $uL/D > 1$, where u is the gas flow rate inside these holes, L is the effective length of the holes, and D is the gas interdiffusion coefficient.

[Detailed Description of the Invention]

[0001]

[Technical Field of the Invention]

The present invention relates to chemical vapour deposition (referred to herein as "CVD"), and in particular it relates to a CVD apparatus suitable for depositing films on large-scale flat panel substrates.

[0002]

[Prior Art]

Hitherto known methods for the production of large-scale liquid crystal displays include methods that use high-temperature polysilicon TFTs (thin film transistors) and methods that use low-temperature TFTs. In liquid crystal display production methods that use low-temperature polysilicon TFTs, there is no need to use expensive substrates such as quartz because all the processes can be performed at low temperature (e.g. 400°C or less).

[0003]

It is also possible to achieve cost reductions by increasing the production yield if the drive circuits for driving the devices in the liquid crystal displays and the like can be built into the substrate at the same time, and since this also has the effect of improving the TFT device

characteristics, it makes it possible to increase the degree of detail and achieve a larger aperture ratio. Consequently, painstaking research is being undertaken with a view to achieving improved performance, and the volume of production
5 itself is also increasing.

[0004]

In the production of liquid crystal displays using low-temperature polysilicon TFTs, plasma CVD is used for the low-temperature deposition of polysilicon oxide films, which
10 are suitable for use as gate insulation films.

[0005]

For such applications, a CVD apparatus proposed in a previous patent application (Patent Application No. H11-157692) involves producing a plasma inside a vacuum
15 enclosure to generate excited active species (referred to herein as "radicals") and using these radicals and a precursor gas to deposit a film on a substrate. Specifically, this apparatus uses a technique whereby a dividing plate plate, having a plurality of holes through
20 which radicals pass, is used to separate the interior of the vacuum enclosure into a plasma discharge space and a film deposition space, radicals are generated from the plasma by introducing a gas into the plasma discharge space, and these radicals are introduced to the film deposition space through
25 the plurality of holes in the abovementioned dividing plate plate; meanwhile, a precursor gas is directly introduced into the film deposition space (i.e., a precursor gas is directly introduced into the film deposition space from outside the vacuum enclosure without coming into contact
30 with the abovementioned plasma or radicals), and the precursor gas is allowed to react with the abovementioned radicals introduced into the film deposition space, whereby a film is deposited on a substrate (e.g., on a glass substrate measuring 370 mm x 470 mm) situated in the film
35 deposition space.

[0006]

An example of a thin-film deposition apparatus used for plasma CVD that uses a conventional dividing plate

(corresponding to reference numeral 24 in Figures 5 and 6) to separate the interior of the vacuum enclosure into a plasma discharge space and a film deposition space is described using Figure 1(a) and (b). Figure 1(a) is a cross-sectional view of the conventional dividing plate, and
5 Figure 1(b) is a plan view of the interior as seen from line X-X in Figure 1(a).

[0007]

This dividing plate consists of a three-plate laminated
10 structure where an intermediate diffusion plate 2 is sandwiched between an upper plate 1 and a gas discharge plate 3 on the film deposition side, and these three plates are fixed at their outer perimeter. The fixing at the outer
15 perimeter of these three plates (upper plate 1, intermediate diffusion plate 2, and gas discharge plate 3 on the film deposition side) can, for example, be achieved by using screw fixing members 9 as shown in the figure, or by welding or the like (not illustrated).

[0008]

The dividing plate consisting of three plates laminated
20 and fixed in this way has spaces provided in the interior thereof - i.e. precursor gas primary diffusion spaces 4 and precursor gas secondary diffusion spaces 5 - and these internal spaces are connected together by intermediate gas
25 distribution holes 6. A precursor gas, which is fed from outside into the vacuum enclosure of the thin-film deposition apparatus, is uniformly diffused as it passes through, in sequential order, precursor gas primary diffusion spaces 4, intermediate gas distribution holes 6,
30 and precursor gas secondary diffusion spaces 5, and is then guided from precursor gas discharge holes 7 toward the film deposition process chamber (the lower part in Figure 1(a)).

[0009]

Meanwhile, radical transit holes 8 are provided in the
35 parts where there are no spaces inside the dividing plate, and the radicals produced in the plasma discharge space (at the top of Figure 1(a)) pass through these radical transit holes 8 and are guided into the film deposition process space (at the bottom of Figure 1(a)).

[0010]

[Problems Addressed by the Invention]

In the abovementioned conventional dividing plate structure, since the plurality of plates constituting the dividing plate (upper plate 1, intermediate diffusion plate 2, and gas discharge plate 3 on the film deposition side) are fixed at the outer perimeter thereof, there have been cases where gaps have appeared between plates (e.g., between upper plate 1 and intermediate diffusion plate 2, or between intermediate diffusion plate 2 and gas discharge plate 3 on the film deposition side) in regions closer to the central part of the plates, which are not fixed. In such cases, the radicals that pass through the radical transit holes 8 running through the said plurality of plates (upper plate 1, intermediate diffusion plate 2, and gas discharge plate 3 on the film deposition side) may penetrate from these gaps into the interior of the dividing plate. If this happens, the radicals that have penetrated through the said gaps will come into contact with the precursor gas in parts such as precursor gas primary diffusion spaces 4 and precursor gas secondary diffusion spaces 5, and a reaction will take place inside the dividing plate; the products of this reaction can lead to the generation of particles, and this has led to problems in that it becomes impossible to provide an adequate supply of radicals into the film deposition process space.

[0011]

The present invention has been made to solve problems such as these, and aims to provide a thin-film deposition apparatus incorporating a dividing plate equipped with radical passage holes that has improved bonding between the plurality of plates constituting the dividing plate, and wherein - when radicals pass through from the plasma discharge space to the film deposition process space - there is no danger of radicals penetrating into the interior of the dividing plate.

[0012]

[Means of Solving the Problems]

To solve the abovementioned problems, a thin-film deposition apparatus according to the present invention is a thin-film deposition apparatus that produces a plasma inside a vacuum enclosure to generate active species and uses these active species and a precursor gas to deposit a film on a substrate, and is configured as follows.

[0013]

In a thin-film deposition apparatus according to the present invention, the interior of the vacuum reaction chamber is divided by a dividing plate into a plasma discharge space and a film deposition process space; this dividing plate has internal spaces that are separated from the abovementioned plasma discharge space and connect with the abovementioned film deposition process space, and a plurality of holes that pass through from the abovementioned plasma discharge space to the film deposition process space. A gas is introduced into the abovementioned plasma discharge space, where radicals are generated by the plasma, and these radicals are introduced into the abovementioned film deposition process space via the plurality of holes in the abovementioned dividing plate. Also, in this apparatus, a precursor gas is introduced into the abovementioned film deposition process space (i.e., the precursor gas is introduced directly into the film deposition process space from outside the vacuum enclosure, without coming into contact with the abovementioned plasma or radicals), and in the film deposition process space, the abovementioned radicals and precursor gas introduced thereto react together and a film is thereby deposited on a substrate positioned in the film deposition process space.

[0014]

Here, a film deposition apparatus according to the present invention is characterized in that, in the abovementioned dividing plate, the plurality of laminated plates are fixed or connected together by securely bonding them over the entire area of their interfacial surfaces.

[0015]

Above, where it says the plurality of laminated plates are fixed or connected together by securely bonding them over the entire area of their interfacial surfaces, this means that apart from the parts where the abovementioned internal spaces and the abovementioned plurality of holes are provided in the dividing plate, the plates are fixed or connected together in such a way that they are securely bonded together at the mutually contacting surfaces of mutually contacting plates.

[0016]

In this way, since the plurality of laminated plates constituting the dividing plate are fixed or connected by securely bonding them together over the entire area of their interfacial surfaces, it is possible to prevent the penetration of radicals from the plurality of holes connecting the plasma discharge space with the film deposition space, which are formed by piercing through the abovementioned plurality of laminated plates, and it is thereby possible to prevent the radicals and precursor gas from coming into contact with each other inside the dividing plate.

[0017]

Above, where it says fixed by securely bonding over the entire area of their interfacial surfaces, this means that instead of just fixing the plates of the dividing plate together at the outer periphery thereof, it is possible to fix the plates together with metal fixings (e.g. rivets 11, metal fixings 12), which have holes in their interior to connect the plasma discharge space with the film deposition process space, located at positions over the entire dividing plate area, except where the abovementioned interior spaces are provided inside the dividing plate, in such a way that the film deposition performance - e.g., the film deposition rate or uniformity - is made as uniform as possible.

[0018]

Also, where it says connected together by securely bonding over the entire area of their interfacial surfaces, this means that instead of just fixing the plates of the

dividing plate together at the outer periphery thereof, it is possible to connect the plates together by vacuum soldering, pressure welding or the like at the interfacial surfaces over the entire dividing plate, except at parts
5 where the abovementioned plurality of holes connecting the plasma discharge space and the film deposition process space - which are disposed at positions chosen so as to optimize the film deposition performance such as the film deposition rate and uniformity - and the abovementioned internal spaces
10 are provided inside the dividing plate.

[0019]

In the abovementioned thin-film deposition apparatus according to the present invention, dividing plate 24 adopts a structure wherein, as shown in Figure 2, the interfacial
15 surfaces of the abovementioned plurality of laminated plates are securely bonded over their entire area by caulking with a plurality of metal fixings (e.g. rivets 11), and the plurality of holes 8 provided in dividing plate 24 can be provided by piercing through the abovementioned metal
20 fixings (e.g. rivets 11).

[0020]

Dividing plate 24 may also adopt a structure wherein, as shown in Figure 3, the interfacial surfaces of the abovementioned plurality of laminated plates are securely
25 bonded over their entire area by screwing the plurality of laminated plates together with a plurality of metal fixings 12 provided with threaded parts on the outside thereof, and the plurality of holes 8, 8 provided in dividing plate 24 can be provided by piercing through the abovementioned metal
30 fixings 12.

[0021]

Furthermore, the interfacial surfaces of the abovementioned plurality of laminated plates in dividing plate 24 may be connected together by securely bonding them
35 over their interfacial entire area, as shown in Figure 4, and the plurality of holes 8, 8 provided in this dividing plate 24 can be formed by piercing through it at positions where the abovementioned internal spaces 4, 5 are not disposed.

[0022]

In all the dividing plate structures in the thin-film deposition apparatus according to the present invention, the plurality of laminated plates constituting the dividing plate are fixed by securely bonding them over the entire area of their interfacial surfaces, and the plurality of holes 8, 8 provided in this dividing plate connecting between the plasma discharge space and the film deposition process space are provided by piercing through each of the plurality of metal fixings used to achieve secure bonding over the entire area of the interfacial surfaces of this plurality of laminated plates. Or alternatively, the abovementioned plurality of holes 8, 8 are formed by piercing through at positions where internal spaces are not disposed in the internal wall, which is connected together by securely bonding a plurality of laminated plates over their entire interfacial area. Therefore, there is no danger of radicals penetrating into the interior of the dividing plate from the holes 8 through which the radicals pass while the radicals pass through from the plasma discharge space to the film deposition process space.

[0023]

In the deposition of a thin film on substrate 21, the film deposition performance, such as the film deposition rate and uniformity, is affected by the holes through which the radicals pass that are provided in dividing plate 24 and disposed at positions opposite substrate 21; specifically, the performance is affected by the number and layout of the holes 8 that connect the plasma discharge space with the film deposition process space. However, in a thin-film deposition apparatus according to the present invention, as mentioned above, it is possible for the holes 8 through which the radicals pass to be provided at the same positions as where the plurality of laminated plates constituting the dividing plate are fixed together by a plurality of metal fixings. Therefore, in the present invention, the layout of the holes 8 through which the radicals pass can be set by giving priority to the film deposition performance over the entire area of dividing plate 24, without being constrained

by the positions at which the plurality of laminated plates constituting dividing plate 24 are fixed together, and it is possible to supply radicals to the film deposition process space from the plasma discharge space without them
5 penetrating into the interior of dividing plate 24.

[0024]

In the abovementioned thin-film deposition apparatus according to the present invention, the abovementioned plurality of holes through which the radicals pass are
10 preferably formed so as to satisfy the condition $uL/D > 1$, where u is the gas flow rate inside these holes, L is the effective length of the holes (in the embodiments shown in Figures 2, 3 and 4, this length is equivalent to the thickness of dividing plate 24), and D is the gas
15 interdiffusion coefficient (the gas interdiffusion coefficient of the two types of gas at both ends of the holes). In a thin-film deposition apparatus according to the present invention, the plasma discharge space and film deposition process space on either side of the dividing
20 plate are only connected through the holes provided in the dividing plate, but as proposed in a previous patent application (Patent Application No. H11-157692), if these holes satisfy the abovementioned condition ($uL/D > 1$), then it is possible to prevent the precursor gas introduced into
25 the film deposition process space from diffusing back towards the plasma discharge space.

[0025]

[Embodiments of the Invention]

Preferred embodiments of the present invention are
30 described below with reference to the attached figures.

[0026]

Figure 2 is a cross-sectional view of a preferred embodiment of dividing plate 24, which divides the vacuum reaction chamber of a thin-film deposition apparatus
35 according to this invention (an example of which is shown in Figure 5) into a plasma discharge space 25 and a film deposition space 26.

[0027]

Dividing plate 24 is formed by fixing together a plurality of laminated plates (upper plate 1, intermediate diffusion plate 2, and gas discharge plate 3 on the film deposition side) by securely bonding them over the entire area of their interfacial surfaces (i.e. between upper plate 1 and intermediate diffusion plate 2, and between intermediate diffusion plate 2 and gas discharge plate 3 on the film deposition side) with a plurality of metal fixings, in this case by caulking with rivets 10, 11.

[0028]

Internal spaces (precursor gas primary diffusion spaces 4, intermediate gas distribution holes 6, source gas secondary diffusion spaces 5) are formed in dividing plate 24, which is made as described above by laminating and fixing upper plate 1, intermediate diffusion plate 2, and gas discharge plate 3 on the film deposition side, in such a way that they are separated from plasma discharge space 25 and connect with film deposition process space 26.

[0029]

Since a structure of this sort is employed, the gas supplied from the outside first enters precursor gas primary diffusion spaces 4 where it is diffused, after which it passes through intermediate gas distribution holes 6 and enters source gas secondary diffusion spaces 5; as it travels along this path, it is uniformly diffused, and it is then guided directly from precursor gas discharge holes 7 into film deposition process space 26, i.e., without coming into contact with the plasma or radicals.

[0030]

Note that in Figure 2, rivets 10 are used to perform fixing at the outer perimeter of the plurality of laminated plates (upper plate 1, intermediate diffusion plate 2, and gas discharge plate 3 on the film deposition side), whereas rivets 11 are used to fix the parts other than the periphery.

[0031]

As Figure 2 shows, in the dividing plate 24 of the thin-film deposition apparatus according to this invention,

the holes 8 that are pierced through it to allow the transit of radicals are provided in the rivets 11 that fix the plurality of laminated plates (upper plate 1, intermediate diffusion plate 2, and gas discharge plate 3 on the film deposition side) together by securely bonding them over the entire area of their interfacial surfaces, except at the outer periphery thereof.

[0032]

As a result, the holes 8 through which the radicals pass are separated from the spaces inside dividing plate 24 (precursor gas primary diffusion spaces 4, intermediate gas distribution holes 6, source gas secondary diffusion spaces 5) by the constituent outer walls of rivets 11, and there is no penetration of radicals into the spaces inside dividing plate 24 while the radicals are introduced from plasma discharge space 25 (at the top of Figure 2) to film deposition process space 26 (at the bottom of Figure 2).

[0033]

Figure 3 shows a cross-sectional view of another preferred embodiment of dividing plate 24, which divides the vacuum reaction chamber of a thin-film deposition apparatus according to this invention into a plasma discharge space 25 (at the top of Figure 3) and a film deposition process space 26 (at the bottom of Figure 3).

[0034]

The dividing plate 24 shown in Figure 3 differs from that shown in Figure 2 in that the rivets 11 are replaced with metal fixings 12 provided with threaded parts on the outside thereof, a plurality of metal fixings 12 being used to screw together the plurality of laminated plates (upper plate 1, intermediate diffusion plate 2, and gas discharge plate 3 on the film deposition side), thereby securely bonding these laminated plates over the entire area of their interfacial surfaces. The holes 8 through which the radicals pass are provided by piercing through metal fixings 12.

[0035]

In the embodiment shown in Figure 3, female threaded parts are provided in gas discharge plate 3 on the film deposition side, and using metal fixings 12 provided with

male threaded parts on the outside at the ends thereof, the metal fixings 12 which are inserted from the top of the plurality of laminated plates (upper plate 1, intermediate diffusion plate 2, and gas discharge plate 3 on the film deposition side) are screwed into the female threaded parts of the abovementioned gas discharge plate 3 on the film deposition side, whereby metal fixings 12 are screwed to the plurality of laminated plates, and the plurality of laminated plates (upper plate 1, intermediate diffusion plate 2, and gas discharge plate 3 on the film deposition side) are thereby fixed by securely bonding them over the entire area of their interfacial surfaces.

[0036]

In the embodiment shown in Figure 3, as in the embodiment shown in Figure 2, as the radicals are guided from plasma discharge space 25 (at the top of Figure 3) to the film deposition process space 26 (at the bottom of Figure 3), the holes 8 through which the radicals pass are separated from the spaces inside dividing plate 24 (precursor gas primary diffusion spaces 4, intermediate gas distribution holes 6, source gas secondary diffusion spaces 5) by the constituent outer walls of metal fixings 12, and while the radicals are introduced from plasma discharge space 25 to film deposition process space 26, there is no penetration of radicals into the spaces inside dividing plate 24.

[0037]

In the embodiment shown in Figure 3, to securely bond the plurality of laminated plates (upper plate 1, intermediate diffusion plate 2, and gas discharge plate 3 on the film deposition side) at their interfacial surfaces, metal fixings 12 provided with threaded parts on the outside thereof are used to screw the abovementioned plurality of laminated plates together, and since these metal fixings 12 can be attached and removed using screw-type connections, the metal fixings 12 can be easily replaced. Therefore, by suitably replacing metal fixings 12, it is easy to modify the diameter or profile of the holes 8 through which the radicals pass.

[0038]

In the embodiments shown in Figures 2 and 3, cases were described in which the length of metal fixings 12 and rivets 11, which have holes 8 through which the radicals pass, matches the thickness of the plurality of laminated plates (upper plate 1, intermediate diffusion plate 2, and gas discharge plate 3 on the film deposition side). However, this does not necessarily have to be the case, and the same action and effects are obtained when the rivets 11 and metal fixings 12 are shorter or longer than the thickness of the plurality of laminated plates.

[0039]

Figure 4 shows a cross-sectional view of a further preferred embodiment of dividing plate 24 where the vacuum reaction chamber of the thin-film deposition apparatus of this invention is separated into a plasma discharge space 25 (at the top of Figure 4) and a film deposition process space 26 (at the bottom of Figure 4).

[0040]

The dividing plate 24 shown in Figure 4 is such that the plurality of laminated plates (upper plate 1, intermediate diffusion plate 2, and gas discharge plate 3 on the film deposition side) are connected together by securely bonding over the entire area of their interfacial surfaces (i.e. between upper plate 1 and intermediate diffusion plate 2, and between intermediate diffusion plate 2 and gas discharge plate 3 on the film deposition side). Internal spaces (precursor gas primary diffusion spaces 4, intermediate gas distribution holes 6, source gas secondary diffusion spaces 5), which are separated from plasma discharge space 25 and connect with film deposition process space 26, are provided in the same way as in the dividing plates 24 shown in Figures 2 and 3, but here the plurality of holes 8, 8 through which the radicals pass are formed by piercing through at positions where the abovementioned internal spaces are not disposed.

[0041]

A method such as vacuum soldering, pressure welding or the like can be used to achieve secure bonding over the

entire area of the interfacial surfaces of the plurality of laminated plates (i.e. between upper plate 1 and intermediate diffusion plate 2, and between intermediate diffusion plate 2 and gas discharge plate 3 on the film deposition side).

[0042]

In Figure 4, the parts identified by reference numeral 13 represent the connecting parts of the interfacial surfaces of upper plate 1, intermediate diffusion plate 2, and gas discharge plate 3 on the film deposition side.

[0043]

As shown in Figure 4, the closely bonded joints made over the entire interfacial surface area of the plates are preferably made by connecting the interfacial surfaces of the plurality of laminated plates (upper plate 1, intermediate diffusion plate 2, and gas discharge plate 3 on the film deposition side) except at the parts where there are internal spaces (precursor gas primary diffusion spaces 4, intermediate gas distribution holes 6, source gas secondary diffusion spaces 5) in dividing plate 24, so as to completely prevent the penetration of radicals into the internal spaces in dividing plate 24 from the holes 8 through which the radicals pass.

[0044]

In the embodiment shown in Figure 4, the plurality of holes 8 through which the radicals pass are formed by piercing through at positions where internal spaces (precursor gas primary diffusion spaces 4, intermediate gas distribution holes 6, source gas secondary diffusion spaces 5) are not disposed in the plurality of laminated plates (upper plate 1, intermediate diffusion plate 2, and gas discharge plate 3 on the film deposition side) that are laminated and connected together by securely bonding them over the entire interfacial surface area, but as mentioned above, since the entire interfacial surfaces of the plurality of laminated plates are connected except at parts where there are internal holes inside dividing plate 24, there is no penetration of the radicals passing through holes 8 into the internal spaces in dividing plate 24, and

there is no danger of radicals coming into contact with the precursor gas in the spaces inside dividing plate 24.

[0045]

With the embodiment shown in Figure 4, since there is
5 no need for members such as rivets 11 or metal fixings 12 to connect together the plurality of laminated plates (upper plate 1, intermediate diffusion plate 2, and gas discharge plate 3 on the film deposition side) by closely bonding them over the entire interfacial area as in the embodiments shown
10 in Figures 2 and 3, it is possible to provide a dividing plate 14 at lower cost. Furthermore, there is no need for a process to attach the plurality of rivets or metal fixings, and it can instead be bonded together with a single operation, allowing a dividing plate to be provided with
15 more stable quality.

[0046]

Note that in each of the abovementioned embodiments, if the holes 8 through which the radicals pass are formed so as to satisfy the condition $uL/D > 1$, where u is the gas flow
20 rate inside these holes 8, L is the effective length of the holes (in the abovementioned embodiments, this length is equivalent to the thickness of dividing plate 24), and D is the gas interdiffusion coefficient (the gas interdiffusion coefficient of the two types of gas at both ends of the
25 holes), then this is advantageous because it is possible to prevent the reverse diffusion of precursor gas introduced into film deposition process space 26 towards plasma discharge space 25.

[0047]

30 Figure 5 shows a rough view of one example of a thin-film deposition apparatus according to the present invention wherein the interior of the vacuum reaction chamber 22 is divided into two chambers by the abovementioned dividing plate 24 shown in Figure 2. The thin-film deposition
35 apparatus shown in Figure 5 deposits a silicon oxide film as a gate insulation film on the surface of a glass substrate 21 as normally used for TFTs (e.g. a glass substrate measuring 370 mm x 470 mm), preferably using silane as the

precursor gas; in this figure, however, dividing plate 24 - which is the characteristic structural part in the thin-film deposition apparatus according to the present invention - is shown expanded in relation to the other parts, and the parts other than dividing plate 24 are only shown in sketch form.

[0048]

An embodiment of the thin-film deposition apparatus according to the present invention is described with reference to Figure 5.

[0049]

The interior of vacuum reaction chamber 22 is divided into two (upper and lower) chambers by a dividing plate 24 (shown in Figure 2) held at ground potential, the upper chamber forming a plasma discharge space 25, and the lower chamber forming a film deposition process space 26. A planar electrode (high frequency electrode) 30 is attached in such a way that the sides around its perimeter come into contact with the upper insulating member 34 of the insulating members 34, 35 interspersed between the upper enclosure constituting vacuum reaction chamber 22, and the lower part of its perimeter comes into contact with the lower insulating member 35. Dividing plate 24 has the desired characteristic thickness and has an overall flat shape, and has a planar profile resembling the horizontal cross-sectional profile of vacuum reaction chamber 22.

[0050]

In the thin-film deposition apparatus shown in Figure 5, the region in which an oxygen plasma 32 is produced inside plasma discharge space 25 is formed from the dividing plate 24, the upper part of the enclosure constituting vacuum reaction chamber 22, and from electrode 30 which is disposed more or less centrally between them. A plurality of holes 30a are formed in electrode 30.

[0051]

A glass substrate 21 is carried into the interior of vacuum reaction chamber 22 by a transfer robot (not illustrated), and is placed on a substrate holding assembly 27 which is held at earth potential, which is the same potential as vacuum enclosure 22. The substrate holding

assembly 27 provided in film deposition process space 26 is already held at the prescribed temperature because a current is made to flow through a heater 28.

[0052]

5 The interior of vacuum reaction chamber 22 is pumped down, depressurized and held at the prescribed vacuum state by a pumping mechanism 23.

[0053]

10 Next, oxygen gas is introduced into plasma discharge space 25 through an oxygen gas inlet pipe 29.

[0054]

15 Meanwhile, the precursor gas (e.g. silane) is introduced into source gas primary diffusion spaces 4 of dividing plate 24 through source gas inlet pipe 33. The silane first enters precursor gas primary diffusion spaces 4 where it is diffused, after which it passes through intermediate gas distribution holes 6 and enters source gas secondary diffusion space 5, during the course of which it is uniformly diffused, and it is then introduced directly
20 into film deposition process space 26 from precursor gas discharge holes 7, i.e., it is introduced into film deposition process space 26 without coming into contact with the plasma or radicals.

[0055]

25 In the abovementioned state, high-frequency electrical power is supplied to electrode 30 via an electric power feed rod 31 which is insulated from the other metal parts. This high-frequency electrical power gives rise to a discharge, and an oxygen plasma 32 is produced around electrode 30
30 inside plasma discharge space 25. By producing oxygen plasma 32, radicals (excited active species), which are a neutral excited species, are produced, and these are introduced into the film deposition process space 26 through the plurality of holes 8, 8 provided in dividing plate 24. Meanwhile, the
35 precursor gas is introduced into film deposition process space 26 through precursor gas primary diffusion spaces 4, intermediate gas distribution holes 6, precursor gas secondary diffusion spaces 5, and precursor gas discharge holes 7.

[0056]

As a result, these radicals come into contact with the precursor gas for the first time inside film deposition process space 26, whereupon a chemical reaction takes place, and silicon oxide material accumulates on the surface of glass substrate 21, whereby a thin film is formed.

[0057]

Figure 6 shows a sketch of another embodiment of a thin-film deposition apparatus according to the present invention, where the interior of vacuum reaction chamber 22 is divided into two chambers by the dividing plate 24 shown in Figure 2. The characteristic constitution of the embodiment shown in Figure 6 is that an insulating member 34 is provided inside the ceiling part of the upper enclosure constituting vacuum reaction chamber 22, and that electrode 30 is disposed therebelow. Electrode 30 has the form of a single-layer planar electrode without holes 30a formed therein as in the case of the embodiment shown in Figure 5. Plasma discharge space 25 is formed by a parallel planar electrode structure from electrode 30 and dividing plate 24. The other constituent parts are essentially the same as in the configuration of the embodiment shown in Figure 5. Therefore, all elements in Figure 6 that are essentially the same as those in Figure 5 are identified with the same reference numerals, and their detailed descriptions will not be repeated here. Furthermore, since the action and advantages of the thin-film deposition apparatus according to the embodiment shown in Figure 6 are the same as those of the abovementioned embodiment shown in Figure 5, their description will not be repeated here.

[0058]

In the abovementioned preferred embodiments of the present invention, the plurality of laminated plates constituting dividing plate 24 are configured from three plates (upper plate 1, intermediate plate 2, and gas discharge plate 3 on the film deposition side), but the embodiments of the present invention are not limited to this number. As long as dividing plate 24 has internal spaces formed therein (e.g. precursor gas primary diffusion spaces

4, intermediate gas distribution holes 6, source gas secondary diffusion spaces 5, and the like) which are separated from the plasma discharge space 25 and connected with film deposition process space 26, it is possible to use
5 a dividing plate 24 that is laminated from two plates that are fixed or connected by securely bonding them over their entire interfacial surface area, and it is also possible to configure dividing plate 24 from 4 or 5 plates.

[0059]

10 Although preferred embodiments of the present invention have been described above with reference to the accompanying figures, the present invention is not limited to these embodiments, and can be modified in a variety of ways within the scope of the art as understood from the Scope of Patent
15 Claims.

[0060]

[Advantages of the Invention]

The present invention relates to a thin-film deposition apparatus wherein the interior of the vacuum reaction
20 chamber is divided into a plasma discharge space and a film deposition process space by a dividing plate having a plurality of holes through which radicals pass, radicals are generated from the plasma by introducing a gas into the plasma discharge space, these radicals are introduced into
25 the film deposition process space through the plurality of holes in the abovementioned dividing plate, and a precursor gas is introduced into the film deposition process space, whereby the abovementioned introduced radicals react with the precursor gas in the film deposition process space and a
30 film is deposited on a substrate disposed in the film deposition process space, and it is able to prevent the radicals produced in the plasma discharge space from penetrating into the spaces inside the dividing plate, which would result in the radicals coming into contact with the
35 precursor gas inside the internal spaces of the dividing plate.

[0061]

That is, with the present invention, it is not only possible to solve the problem of radicals penetrating the

internal spaces of the dividing plate (which causes problems by generating particles that block the precursor gas discharge holes 7), but it is also possible to solve the problem of precursor gas leaking into the plasma discharge space, and as a result it is possible to prevent excessive breakdown of the precursor gas and it is possible to obtain thin films with favourable film quality.

[Brief Description of the Figures]

[Figure 1]

10 (a) A cross-sectional view of the dividing plate in a conventional thin-film deposition apparatus.

(b) A partially simplified plan view of the interior as seen from line X-X in Figure 1(a).

[Figure 2]

15 A partially simplified cross-sectional view of a dividing plate employed in a thin-film deposition apparatus according to the present invention.

[Figure 3]

20 A partially simplified cross-sectional view of another dividing plate employed in a thin-film deposition apparatus according to the present invention.

[Figure 4]

25 A partially simplified cross-sectional view of a further dividing plate employed in a thin-film deposition apparatus according to the present invention.

[Figure 5]

A cross-sectional sketch illustrating one example of a thin-film deposition apparatus according to the present invention.

30 [Figure 6]

A cross-sectional sketch illustrating another example of a thin-film deposition apparatus according to the present invention.

[List of Reference Numerals]

- 35 1 Upper plate
2 Intermediate diffusion plate
3 Gas discharge plate on the film deposition side
4 Precursor gas primary diffusion space

- 5 Precursor gas secondary diffusion space
- 6 Intermediate gas distribution holes
- 7 Precursor gas discharge holes
- 8 Radical connecting holes
- 5 10, 11 Metal fixings (rivets)
- 12 Metal fixings provided with threaded parts
- 13 Joint part
- 21 Glass substrate
- 22 Vacuum reaction chamber
- 10 23 Pumping mechanism
- 24 Dividing plate
- 25 Plasma discharge space
- 26 Film deposition process space
- 27 Substrate holding mechanism
- 15 28 Heater
- 29 Oxygen gas introduction pipe
- 30 Electrode (high frequency electrode)
- 31 Electric power feed rod
- 32 Oxygen plasma
- 20 33 Precursor gas introduction pipe

[Document Title]

Abstract

[Summary]

[Problem] In a thin-film deposition apparatus wherein the interior of the vacuum reaction chamber is divided into a plasma discharge space and a film deposition process space by a dividing plate having a plurality of holes through which radicals pass, radicals are generated from the plasma by introducing a gas into the plasma discharge space, these radicals are introduced into the film deposition process space through the plurality of holes in the abovementioned dividing plate, and a precursor gas is introduced into the film deposition process space, whereby the abovementioned introduced radicals react with the precursor gas in the film deposition process space and a film is deposited on a substrate disposed in the film deposition process space, the aim of this invention is to prevent the radicals produced in the plasma discharge space from penetrating into the spaces inside the dividing plate, which would result in the radicals coming into contact with the precursor gas inside the internal spaces of the dividing plate.

[Means of Solution] The problem is solved by constructing the dividing plate, which divides the interior of the vacuum reaction chamber into a plasma discharge space and a film deposition process space, by fixing or connecting a plurality of laminated plates together by securely bonding them over the entire area of their interfacial surfaces.

[Selected Figure] Figure 6